

BS EN 16806-1:2016



BSI Standards Publication

# **Textiles and textile products — Textiles containing phase change materials (PCM)**

Part 1: Determination of the heat storage  
and release capacity

**National foreword**

This British Standard is the UK implementation of EN 16806-1:2016.

The UK participation in its preparation was entrusted to Technical Committee TCI/80, Chemical testing of textiles.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.  
Published by BSI Standards Limited 2016

ISBN 978 0 580 85046 2

ICS 59.080.30

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2016.

**Amendments/corrigenda issued since publication**

Date	Text affected
------	---------------



EUROPEAN STANDARD

**EN 16806-1**

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2016

ICS 59.080.30

English Version

## Textiles and textile products - Textiles containing phase change materials (PCM) - Part 1: Determination of the heat storage and release capacity

Textiles et produits textiles - Textiles contenant des matériaux à changement de phase (PCM) - Partie 1: Détermination de la capacité de stockage et de dégagement de chaleur

Textilien und textile Erzeugnisse - Phasenwechselmaterialien enthaltende Textilien (PCM) - Teil 1: Bestimmung der Wärmespeicherungs- und Wärmefreisetzungskapazität

This European Standard was approved by CEN on 15 January 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

<b>Contents</b>	<b>Page</b>
<b>European foreword.....</b>	<b>3</b>
<b>1 Scope.....</b>	<b>4</b>
<b>2 Normative references.....</b>	<b>4</b>
<b>3 Terms and definitions .....</b>	<b>4</b>
<b>4 Principle of test.....</b>	<b>5</b>
<b>5 Test equipment, reagents and materials.....</b>	<b>5</b>
<b>6 Test specimens.....</b>	<b>5</b>
<b>7 DSC test procedure .....</b>	<b>7</b>
<b>8 Calculation of test results.....</b>	<b>7</b>
<b>9 Test report.....</b>	<b>8</b>
<b>Bibliography.....</b>	<b>10</b>



## European foreword

This document (EN 16806-1:2016) has been prepared by Technical Committee CEN/TC 248 “Textiles and textile products”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2016, and conflicting national standards shall be withdrawn at the latest by September 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

EN 16806, Textiles and textile products — Textiles containing phase change materials (PCM), consists of the following parts:

- *Textiles and textile products — Textiles containing phase change materials (PCM) — Part 1: Determination of the heat storage and release capacity*
- *Textiles and textile products — Textiles containing phase change materials (PCM) — Part 2: Determination of the heat transfer using a dynamic method*
- *Textiles and textile products — Textiles containing phase change materials (PCM) — Part 3: Determination of the heat transfer between the user and the product.*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This part of EN 16806 specifies a test method for the determination of the heat storage and heat release capacity and the phase change temperatures of textile fibres, yarns and fabrics (woven and knitted fabrics, nonwovens) containing phase change materials (PCM). The test method can also be applied for pure or micro-encapsulated PCM.

This part of EN 16806 does not apply to the determination of the heat transfer properties of textile fabrics (woven and knitted fabrics, nonwovens) containing phase change materials, for which part 2 of EN 16806 applies.

This part of EN 16806 does not apply to determining the heat transfer between the user and the product for textile products, e.g. garments, mattresses, etc. made with PCM containing materials, for which part 3 of EN 16806 applies.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12127, *Textiles - Fabrics - Determination of mass per unit area using small samples*

EN ISO 139, *Textiles - Standard atmospheres for conditioning and testing (ISO 139)*

EN ISO 11357-1, *Plastics - Differential scanning calorimetry (DSC) - Part 1: General principles (ISO 11357-1)*

EN ISO 11357-3, *Plastics - Differential scanning calorimetry (DSC) - Part 3: Determination of temperature and enthalpy of melting and crystallization (ISO 11357-3)*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

**3.1**  
**phase change material**  
**PCM**  
a substance which is capable of storing and releasing thermal energy in the form of latent heat (enthalpy), over a specific temperature range during which the material changes phase (from solid to liquid or from liquid to solid), thus buffering external temperature changes

Note 1 to entry: These temperature ranges are usually close to skin temperature.

**3.2**  
**pure PCM**  
PCM in its free form

**3.3**  
**micro-encapsulated PCM**  
PCM contained in a spherically shaped particle with a closed shell and having a diameter in the range of 1 µm to 1 mm



### 3.4

#### **textile containing PCM**

textile containing the phase change material inside the fibres or yarns; or having the PCM applied to the fibre, yarn or textile surface

### 3.5

#### **phase change temperature**

peak temperature at which the PCM changes either from the solid to the liquid (melting temperature) or from the liquid to the solid state (crystallisation temperature)

Note 1 to entry: Ideally, the two phase change temperatures should be identical, but in reality a difference will be observed as often material mixtures are used.

## **4 Principle of test**

This test determines the enthalpy of fusion and of crystallization, as well as the phase change temperatures of fibres, yarns and fabrics containing PCM.

A differential scanning calorimetry (DSC) method is used. The difference between the rate of heat flow into a specimen and that into a reference crucible is measured as a function of temperature and/or time while the specimen and the reference are subjected to the same temperature control programme.

## **5 Test equipment, reagents and materials**

The DSC test equipment described in EN ISO 11357-1 shall be used.

Open aluminium crucibles shall be used to ensure an isobaric measurement. It is recommended to put a lid on the crucible but without sealing it hermetically.

The test equipment shall be calibrated periodically in accordance with the instructions and recommendations of the equipment manufacturer, i.e. with respect to the use and shelf life of calibration standards. The calibration procedure of EN ISO 11357-1 shall be followed. Calibration materials should be chosen with a transition temperature as close as possible to phase change temperature of the PCM. The heating rate shall be 5 °C/min.

NOTE A suitable calibration material is phenyl salicylate (CAS 118-55-8), with a melting temperature of 41,79 °C and an enthalpy of fusion of  $(89,4 \pm 0,4)$  J/g. Other reference materials can be recommended by the suppliers.

## **6 Test specimens**

### **6.1 Sample conditioning**

Samples shall be conditioned in the standard atmosphere according to EN ISO 139 (20 °C  $\pm$  2 °C and 65 % RH  $\pm$  4 % RH) for at least 24 h before determining the mass per unit area.

This conditioning only applies to textile materials containing PCM and the dried micro-encapsulated PCM. It does not apply to the pure PCM.

### **6.2 Sampling and specimen preparation**

#### **6.2.1 General**

The specimen shall be representative of the sample being examined and shall be prepared and handled with care. Particular care shall be taken to avoid any contamination of the specimen. If the specimen crucible is closed with a lid, this shall not cause any deformation of the bottom of the crucible. Good



thermal contact between the specimen and crucible and between the crucible and holder shall be ensured.

The mass of the DSC test specimens shall be between 10 and 40 mg, with 10 mg being recommended. It may be necessary for low weight fabrics to put several layers in the same crucible to get the required mass. The tolerance on the weight should be as described in EN ISO 11357-1. A lid shall be pressed on the crucible to ensure a good contact between the textile specimen and the bottom of the crucible. For very thin fabrics or for bulky, fluffy materials it may be necessary to stack, fold or compress the textile material to obtain a good thermal contact with the bottom of the crucible. Care shall be taken to allow pressure release during the measurement (isobaric measurement condition).

A new crucible and lid shall be used for each specimen.

NOTE Each DSC instrument has its own shape of crucibles and its own press to put the lid on the crucible. Crucibles are not interchangeable.

### **6.2.2 Pure PCM**

Three specimens shall be prepared.

Pre-weigh the empty crucible and its lid.

Pre-heat the PCM sample to 60 °C so that it is in the liquid state. Collect one representative specimen of pure PCM through a micro-pipette with a volume range between 10 to 20 µL. Carefully deposit the PCM into the crucible so that the bottom of the crucible is completely covered, without overfilling. Carefully place the lid when sealing the crucible in order to avoid spilling of the PCM.

Leave the crucible at room temperature in a desiccator for 20 min to solidify the PCM.

Weigh the filled crucible and determine the weight of the PCM.

### **6.2.3 Micro-encapsulated PCM**

The micro-encapsulated PCM product shall be dried at 60 °C for at least 24 h to remove all water. The micro-encapsulated PCM product shall then be conditioned as described in 6.1.

The sample size should be sufficient to prepare five DSC specimens. Three of them shall be tested; if the coefficient of variation is too high (see 7.2) the other two shall also be tested.

Prepare five DSC specimens in accordance with 6.2.1.

### **6.2.4 Fibres and yarns**

Five representative test specimens shall be taken from the fibre or yarn sample and prepared in accordance with 6.2.1. Three of them shall be tested; if the coefficient of variation is too high (see clause 7.2) the other two specimen shall also be tested.

### **6.2.5 Fabrics**

Test specimens shall be taken from a fabric sample of at least 50 cm length over the entire width of the fabric.

From this fabric sample, five specimens shall be taken to determine the mass per unit area of the fabric in accordance with EN 12127.

Representative test specimens for the DSC analysis shall be taken from three of the five specimens used for the determination of mass per unit area. One DSC specimen shall be taken from each of these three mass specimens. The two remaining mass specimens shall be kept for additional tests in case of excessive scattering of test results or if test results are discarded.

Care should be taken to ensure representativeness of the specimens. In the case of multi-layered (e.g. coated, laminated or stacked) substrates, specimen shall be taken in a manner that includes all layers of



the sample. In the case of heterogeneous samples, specimens with different composition shall be taken. As many different zones as possible shall be sampled taking into account the relative surface area of the fabric.

Deviations from the above sampling procedures may be agreed on by the involved parties. This deviating sampling procedure then shall be clearly described in the report.

## 7 DSC test procedure

### 7.1 General

Test specimens and reference specimens are subjected to a temperature control programme, which contains a heating-cooling-heating thermal cycle at a rate of 5 °C/min under a controlled inert atmosphere.

The cycling shall be performed between a low temperature,  $T_{\text{low}}$ , of –20 °C and a high temperature,  $T_{\text{high}}$ , of 60 °C. The base line (as defined in 7.2) before and after the phase change transition peak shall be stable over a range of 20 °C. If this condition is not met, the interval between  $T_{\text{low}}$  and  $T_{\text{high}}$  shall be extended.

### 7.2 Test sequence

The test procedures as defined in EN ISO 11357-1 and EN ISO 11357-3 shall be applied unless otherwise specified hereafter.

A heating and cooling rate of 5 °C/min shall be used.

The test shall be performed on three specimens.

The test procedure shall be performed as follows:

- Choose the testing range as defined in 7.1.
- Perform a first heating step from  $T_{\text{low}}$  to  $T_{\text{high}}$ , followed by an isotherm at  $T_{\text{high}}$  for 2 min.
- Then perform a first cooling step from  $T_{\text{high}}$  to  $T_{\text{low}}$ , followed by an isotherm at  $T_{\text{low}}$  for 2 min.
- Then perform a second heating step from  $T_{\text{low}}$  to  $T_{\text{high}}$ .

If the coefficient of variation on these three test results exceeds 20 % (see Clause 8), two additional measurements shall be performed.

NOTE Inhomogeneous samples as well as samples containing significant amounts of water or that show artefacts in the temperature range of the measurement cycle (e.g. glass transitions or phase transitions in the substrate material) can result in a high coefficient of variation.

## 8 Calculation of test results

### 8.1 General

For each DSC specimen:

- based on the recorded second heating cycle, determine the enthalpy of fusion in J/g (as defined in EN ISO 11357-3);
- based on the recorded cooling cycle, determine the enthalpy of crystallization in J/g (as defined in EN ISO 11357-3);



- based on the recorded second heating cycle, determine the extrapolated onset melting temperature, the peak melting temperature (phase change temperature on heating) and the extrapolated end melting temperature (as defined in EN ISO 11357-3);
- based on the recorded cooling cycle, determine the extrapolated onset crystallization temperature, the peak crystallization temperature (phase change temperature on cooling) and the extrapolated end crystallization temperature (as defined in EN ISO 11357-3).

The heat of fusion and heat of crystallization should be similar (within 10 %). If this is not the case, the area of integration shall be checked and adjusted.

Calculation of the average enthalpy of fusion and crystallization:

For each of the three specimens, calculate the average enthalpy per unit mass for crystallization and of fusion.

## **8.2 Calculation of the average enthalpy of fusion and crystallization per unit area (Fabrics)**

Record the mass per unit area ( $\text{g/m}^2$ ) to three significant digits for each individual DSC specimen, as determined in 6.2.5, as well as the mean value and the coefficient of variation, if required. Calculate the average mass per unit area for the sample from these individual values.

Calculate the average enthalpy of fusion/ crystallization per unit area as the ratio of the average enthalpy of fusion/ crystallization per unit mass and the average mass per unit area for the sample.

## **9 Test report**

The test report shall contain the following elements:

- a) reference to this part of the standard;
- b) identification of the test lab;
- c) identification of the sample and the material;
- d) test conditions, including;
  - 1) date;
  - 2) particulars of specimen preparation;
  - 3) reference of calibration standard and frequency of calibration.
- e) type of DSC instrument used (heat flux or power compensated), as well as the instrument model and manufacturer;
- f) number of specimens;
- g) test results, in the correct number of significant digits, as determined by the standard deviation;
  - 1) the enthalpy of fusion, the enthalpy of crystallization, the average results and standard deviations for this;
  - 2) the mass of the fabric in  $\text{g/m}^2$  and the calculated average result for the heat storage and release capacity in  $\text{J/m}^2$ ;



For high standard deviations it is useful to report 3 significant digits, even though it should be less according to the standard deviation.

3) the measurement curve with interpretation including:

- i) the extrapolated onset melting temperature (in °C);
- ii) the peak melting temperature (phase change temperature) (in °C);
- iii) the extrapolated onset crystallization temperature (in °C);
- iv) the peak crystallization temperature (in °C).

h) other remarks and observations;

i) deviations from this standard;

The test report may additionally include the following results:

j) individual results for the enthalpy of fusion;

k) individual results enthalpy of crystallization;

l) individual results for the fabric weight;

m) for extended peaks: to report the enthalpy for temperature intervals within the complete peak, as agreed with the customer.

## Bibliography

- [1] “Standards, Calibration, and Guidelines in Microcalorimetry – Part 2: Calibration Standards for Differential Scanning Calorimetry (IUPAC Technical Report – Della Gatta et Al) © 2006 IUPAC, Pure and Applied Chemistry 78, 1455–1476, Table 3
- [2] ISO/TR 11827, *Textiles — Composition testing — Identification of fibres*
- [3] CEN/TR 16298, *Textiles and textile products - Smart textiles - Definitions, categorisation, applications and standardization needs*





# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](https://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](https://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](https://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](https://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK